

# FinTOP BG – Tall Oil Pitch

## General Information

FinTOP BG is fully biobased material that can be used for example in paving and roofing industry replacing fossil raw materials such as bitumen.

## Typical values

Property	Typical value	Specification	Method
Acid Value, mg KOH/g	75	max 85	ASTM D465
Rosin Acids, %	35	max 40	ASTM D1240
Viscosity (80°C), mPas	2000-2500		ASTM D2196

## Delivery and storage

Product is in liquid form at storage temperature of ~80 °C and it can be delivered in ISO-container or road tanker.

FinTOP BG should be stored 70-90 °C and the recommended unloading temperature is about 80 °C.

In case the product is cooled down, it becomes high viscous. When heating the material up to 70-90 °C, it will restore viscosity low enough for pumping.

**EC number** 232-414-4  
**CAS number** 8016-81-7  
**HS-code** 3807 00  
**Reach Reg. No.** 01-2119489491-29-0018

In all applications of this product, it is the sole responsibility of the buyer to respect and comply with any valid intellectual property rights of third parties.